Ph: 13 BRICK | 13 2742
www.australbricks.com.au

PRODUCT DATA SHEET

Date: August 2009	Product Name: Chestnut - Bowral® London Range	
Product Code: 8800-1	image unavailable	
Description:		
Manufactured: Bowral, NSW		
Application:		

Typical Properties	
Length (mm)	230mm
Width (mm)	114mm
Height (mm)	65mm
Dimensional Category	DPA1
Average Weight / Unit	3.5 kg
Units per Square Metre	37
Pack Size	700
Characteristic Breaking Load	>10 kN
24 Hour Cold Water Absorption	<10 %
Mean Abrasion Resistance	<12 cm^3
Estimated 15 year Coefficient of Expansion (e factor)	<1.0mm/m
Slip Resistance Category	V
Durability Class	Exposure Grade

This data represents average results from commercial production lots. If specific test results are required, samples should be taken from current production lots.
AUSTRALIAN STANDARD TEST METHODS AS/NZS 4456 ARE USED AS APPLICABLE.

Specifications

Product Code	Product Name	Dimensions			Dimensional Category	Weight (kg)	Breaking Load (kN)	e' Factor (mm/m)	Durability	Abrasion Resistance (cm3)	Slip Resistance Category
		Length (mm)	Width (mm)	Height (mm)							
8830-1	Regency Grey	230	114	65	DPA1	3.5	>10	<0.5	Exposure	<7	V
8800-1	Chestnut	230	114	65	DPA1	3.5	>10	<1.0	Exposure	<12	V
8720-1	Maple	230	114	65	DPA1	3.5	>10	<0.5	Exposure	<12	V
8740-1	Silver Sand	230	114	65	DPA1	3.5	>8	<0.5	Exposure	<12	V

Ph: 13 BRICK | 13 2742
www.australbricks.com.au

PRODUCT DATA SHEET

Date: August 2009	Product Name: Maple - Bowral® London Range	
Product Code: 8720-1	image unavailable	
Description:		
Manufactured: Bowral, NSW		
Application:		

Typical Properties	
Length (mm)	230mm
Width (mm)	114mm
Height (mm)	65mm
Dimensional Category	DPA1
Average Weight / Unit	3.5 kg
Units per Square Metre	37
Pack Size	700
Characteristic Breaking Load	>10 kN
24 Hour Cold Water Absorption	<10 %
Mean Abrasion Resistance	<12 cm^3
Estimated 15 year Coefficient of Expansion (e factor)	<0.5 mm/m
Slip Resistance Category	V
Durability Class	Exposure Grade

This data represents average results from commercial production lots. If specific test results are required, samples should be taken from current production lots.
AUSTRALIAN STANDARD TEST METHODS AS/NZS 4456 ARE USED AS APPLICABLE.

Specifications

Product Code	Product Name	Dimensions			Dimensional Category	Weight (kg)	Breaking Load (kN)	e' Factor (mm/m)	Durability	Abrasion Resistance (cm3)	Slip Resistance Category
		Length (mm)	Width (mm)	Height (mm)							
8830-1	Regency Grey	230	114	65	DPA1	3.5	>10	<0.5	Exposure	<7	V
8800-1	Chestnut	230	114	65	DPA1	3.5	>10	<1.0	Exposure	<12	V
8720-1	Maple	230	114	65	DPA1	3.5	>10	<0.5	Exposure	<12	V
8740-1	Silver Sand	230	114	65	DPA1	3.5	>8	<0.5	Exposure	<12	V

Ph: 13 BRICK | 13 2742
www.australbricks.com.au

PRODUCT DATA SHEET

Date: August 2009	Product Name: Regency Grey - Bowral® London Range	
Product Code: 8830-1	image unavailable	
Description:		
Manufactured: Bowral, NSW		
Application:		

Typical Properties	
Length (mm)	230mm
Width (mm)	114mm
Height (mm)	65mm
Dimensional Category	DPA1
Average Weight / Unit	3.5 kg
Units per Square Metre	37
Pack Size	700
Characteristic Breaking Load	>10 kN
24 Hour Cold Water Absorption	<10 %
Mean Abrasion Resistance	<7 cm^3
Estimated 15 year Coefficient of Expansion (e factor)	<0.5 mm/m
Slip Resistance Category	V
Durability Class	Exposure Grade

This data represents average results from commercial production lots. If specific test results are required, samples should be taken from current production lots.
AUSTRALIAN STANDARD TEST METHODS AS/NZS 4456 ARE USED AS APPLICABLE.

Specifications

Product Code	Product Name	Dimensions			Dimensional Category	Weight (kg)	Breaking Load (kN)	e' Factor (mm/m)	Durability	Abrasion Resistance (cm3)	Slip Resistance Category
		Length (mm)	Width (mm)	Height (mm)							
8830-1	Regency Grey	230	114	65	DPA1	3.5	>10	<0.5	Exposure	<7	V
8800-1	Chestnut	230	114	65	DPA1	3.5	>10	<1.0	Exposure	<12	V
8720-1	Maple	230	114	65	DPA1	3.5	>10	<0.5	Exposure	<12	V
8740-1	Silver Sand	230	114	65	DPA1	3.5	>8	<0.5	Exposure	<12	V

Ph: 13 BRICK | 13 2742
www.australbricks.com.au

PRODUCT DATA SHEET

Date: August 2009	Product Name: Silver Sand - Bowral® London Range	
Product Code: 8740-1	image unavailable	
Description:		
Manufactured: Bowral, NSW		
Application:		

Typical Properties	
Length (mm)	230mm
Width (mm)	114mm
Height (mm)	65mm
Dimensional Category	DPA1
Average Weight / Unit	3.5 kg
Units per Square Metre	37
Pack Size	700
Characteristic Breaking Load	>8 kN
24 Hour Cold Water Absorption	<10 %
Mean Abrasion Resistance	<12 cm^3
Estimated 15 year Coefficient of Expansion (e factor)	<0.5 mm/m
Slip Resistance Category	V
Durability Class	Exposure Grade

This data represents average results from commercial production lots. If specific test results are required, samples should be taken from current production lots.
AUSTRALIAN STANDARD TEST METHODS AS/NZS 4456 ARE USED AS APPLICABLE.

Specifications

Product Code	Product Name	Dimensions			Dimensional Category	Weight (kg)	Breaking Load (kN)	e' Factor (mm/m)	Durability	Abrasion Resistance (cm3)	Slip Resistance Category
		Length (mm)	Width (mm)	Height (mm)							
8830-1	Regency Grey	230	114	65	DPA1	3.5	>10	<0.5	Exposure	<7	V
8800-1	Chestnut	230	114	65	DPA1	3.5	>10	<1.0	Exposure	<12	V
8720-1	Maple	230	114	65	DPA1	3.5	>10	<0.5	Exposure	<12	V
8740-1	Silver Sand	230	114	65	DPA1	3.5	>8	<0.5	Exposure	<12	V