

Range: Bowral 300

Colour: Embassy Red

SKU: bowral300_embassy_red

Technical Data

Length (mm)	300	Initial Rate of Absorption (IRA) (kg/m ² min)	4.0-6.0
Width (mm)	110	Coefficient of Expansion e'Factor (mm/m)	<1.0
Height (mm)	50	Durability Class	Exposure Grade
Dimensional Category	DW1	Liability to Efflorescence	Slight
Average Weight / Unit (kg)	3.4	Lime Pitting Liability	Slight
Core Volume (%)	Solid	Solar Absorptance Rating	0.73
Units per Square Metre	60	Solar Absorption	0.73
Pack Size	384	LRV	11.1
Characteristic Unconfined Compressive Strength (f 'uc) MPa	>8	Basix	dark
Maximum Cold Water Absorption (%)	<10	Solar Absorption	0.73

A BRAND OF

BRICKWORKS