

Range: Bowral 300

Colour: Hereford Bronze

SKU: bowral300_hereford_bronze

Technical Data

Length (mm)	300	Initial Rate of Absorption (IRA) (kg/m ² min)	4.0-6.0
Width (mm)	110	Coefficient of Expansion e'Factor (mm/m)	<1.0
Height (mm)	50	Durability Class	Exposure Grade
Dimensional Category	DW1	Liability to Efflorescence	Slight
Core Volume (%)	Solid	Lime Pitting Liability	Slight
Units per Square Metre	60	Solar Absorption	0.76
Pack Size	384	LRV	17.3
Characteristic Unconfined Compressive Strength (f 'uc) MPa	>8	Solar Absorption	0.76
Maximum Cold Water Absorption (%)	<15		

A BRAND OF

BRICKWORKS