

Range: Bowral 50

Colour: Renovation Gertrudis Brown

SKU: 280070042250000125150

Technical Data

Length (mm)	230	Initial Rate of Absorption (IRA) (kg/m ² min)	1.0-8.0
Width (mm)	110	Coefficient of Expansion e'Factor (mm/m)	<1.2
Height (mm)	50	Durability Class	Exposure Grade
Dimensional Category	DW1	Liability to Efflorescence	Nil to slight
Average Weight / Unit (kg)	2.5	Lime Pitting Liability	Nil to slight
Core Volume (%)	Solid	Solar Absorption	0.85
Units per Square Metre	69.5	LRV	12.9
Pack Size	700	Basix	dark
Characteristic Unconfined Compressive Strength (f 'uc) MPa	>8	Place of Manufacture	New South Wales
Maximum Cold Water Absorption (%)	<15	Product Warranty	100 Years

A BRAND OF

BRICKWORKS