

Range: Bowral 300

Colour: Embassy Red

SKU: bowral300_embassy_red

Technical Data

| | | | |
|--|-------|--|----------------|
| Length (mm) | 300 | Initial Rate of Absorption (IRA) (kg/m ² min) | 4.0-6.0 |
| Width (mm) | 110 | Coefficient of Expansion e'Factor (mm/m) | <1.0 |
| Height (mm) | 50 | Durability Class | Exposure Grade |
| Dimensional Category | DW1 | Liability to Efflorescence | Slight |
| Core Volume (%) | Solid | Lime Pitting Liability | Slight |
| Units per Square Metre | 60 | Solar Absorption | 0.73 |
| Pack Size | 384 | LRV | 11.1 |
| Characteristic Unconfined Compressive Strength (f 'uc) MPa | >8 | Basix | dark |
| Maximum Cold Water Absorption (%) | <10 | Solar Absorption | 0.73 |

A BRAND OF

BRICKWORKS