

Bowral Remastered Range Technical Data Sheet

BRICKWORKS

Product Range	Product Name	Dimension Illustration	Swatch	State	Length (mm)	Width (mm)	Height (mm)	Dimensional Category	Units per Square Metre	Pack Size	Characteristic Unconfined Compressive Strength (f <sub>uc</sub> ) MPa	Maximum Cold Water Absorption (%)	Initial Rate of Absorption (IRA) (kg/m <sup>2</sup> min)	Coefficient of Expansion Factor (mm/m)	Durability Class	Liability to Efflorescence	Lime Pitting Liability
Bowral Remastered	Oxley			NSW	230	110	76	DW1	48.5	500	>8	15	1 to 8	1.2	Exposure Grade	Slight	Slight
Bowral Remastered	Moss Vale			NSW	230	110	76	DW1	48.5	500	>8	15	1 to 8	1.2	Exposure Grade	Slight	Slight
Bowral Remastered	Westow			NSW	230	110	76	DW1	48.5	500	>8	15	1 to 8	1.2	Exposure Grade	Slight	Slight
Bowral Remastered	St Jude			NSW	230	110	76	DW1	48.5	500	>8	15	1 to 8	1.2	Exposure Grade	Slight	Slight

This Data represents average results from commercial production lots.  
If specific test results are required, sample should be taken from current production lots.  
AUSTRALIAN STANDARD TEST METHODS AS/NSZ 4456 ARE USED AS APPLICABLE.