

# Bowral Remastered Range Technical Data Sheet

# BRICKWORKS

Product Range	Product Name	Dimension Illustration	Swatch	State	Length (mm)	Width (mm)	Height (mm)	Dimensional Category	Average Weight / Unit (kg)	Core Volume (%)	Units per Square Metre	Pack Size	Characteristic Unconfined Compressive Strength (f <sub>uc</sub> ) MPa	Liability to Efflorescence	Lime Pitting Liability	FRL
Bowral Remastered	Oxley			NSW	230	110	76	DW1	3.8	Solid	48.5	384	>8	Slight	Slight	180/180/90
Bowral Remastered	Westow			NSW	230	110	76	DW1	3.8	Solid	48.5	384	>8	Slight	Slight	180/180/90
Bowral Remastered	Moss Vale			NSW	230	110	76	DW1	3.8	Solid	48.5	384	>8	Slight	Slight	180/180/90
Bowral Remastered	St Jude			NSW	230	110	76	DW1	3.8	Solid	48.5	384	>8	Slight	Slight	180/180/90
Bowral Remastered	Gibraltar			NSW	230	110	76	DW1	3.8	Solid	48.5	384	>12	Slight	Slight	180/180/90

This Data represents average results from commercial production lots.

If specific test results are required, sample should be taken from current production lots.

AUSTRALIAN STANDARD TEST METHODS AS/NSZ 4456 ARE USED AS APPLICABLE.

Please note: FRL applies up to 3m high - restrained on top and bottom.

BOWRAL BRICKS