























Bowral 300 Range Technical Data Sheet

BRICKWORKS

Product Range	Product Name	Dimension Illustration	Swatch	State	Length (mm)	Width (mm)	Height (mm)	Dimensional Category	Units per Square Metre	Pack Size	Characteristic Unconfined Compressive Strength (f _{uc}) MPa	Maximum Cold Water Absorption (%)	Initial Rate of Absorption (IRA) (kg/m ² min)	Coefficient of Expansion Factor (mm/m)	Durability Class	Liability to Efflorescence	Lime Pitting Liability	LRV
Bowral 300	Bowral Blue			SA	300	110	50	DW1	60	384	>8	15	1.0-8.0	1.2	Exposure Grade	Nil to slight	Nil to slight	8.3
Bowral 300	Bowral Brown			SA	300	110	50	DW1	60	384	>12	10	4.0-6.0	0.8	Exposure Grade	Slight	Slight	14.7
Bowral 300	Brahman Granite			SA	300	110	50	DW1	60	384	>8	15	1.0-8.0	1.2	Exposure Grade	Nil to slight	Nil to slight	11.6
Bowral 300	Capitol Red			SA	300	110	50	DW1	60	384	>8	15	1.0-8.0	1.2	Exposure Grade	Nil to slight	Nil to slight	14.9
Bowral 300	Chillingham White			SA	300	110	50	DW1	60	384	>8	15	1.0-8.0	1.2	Exposure Grade	Nil to slight	Nil to slight	56.1
Bowral 300	Gertrudis Brown			SA	300	110	50	DW1	60	384	>8	15	1.0-8.0	1.2	Exposure Grade	Nil to slight	Nil to slight	11.9
Bowral 300	Murray Grey			SA	300	110	50	DW1	60	384	>8	15	1.0-8.0	1.2	Exposure Grade	Nil to slight	Nil to slight	17.3
Bowral 300	Renovation Gertrudis Brown			SA	300	110	50	DW1	60	384	>8	15	4.0-6.0	1.0	Exposure Grade	Slight	Slight	12.9
Bowral 300	Simmental Silver			SA	300	110	50	DW1	60	384	>8	15	1.0-8.0	1.2	Exposure Grade	Nil to slight	Nil to slight	28.5
Bowral 300	Embassy Red			SA	300	110	50	DW1	60	384	>8	10	4.0-6.0	1.0	Exposure Grade	Slight	Slight	11.1
Bowral 300	Hereford Bronze			SA	300	110	50	DW1	60	384	>8	15	4.0-6.0	1.0	Exposure Grade	Slight	Slight	17.3

This Data represents average results from commercial production lots.

If specific test results are required, sample should be taken from current production lots.

AUSTRALIAN STANDARD TEST METHODS AS/NSZ 4456 ARE USED AS APPLICABLE.

BOWRAL BRICKS