

Range: Bowral 50

Colour: Embassy Red

SKU: bowral_50_embassy_red

Technical Data

Length (mm)	230	Maximum Cold Water Absorption (%)	<15
Width (mm)	110	Initial Rate of Absorption (IRA) (kg/m ² min)	4.0-6.0
Height (mm)	50	Coefficient of Expansion e'Factor (mm/m)	<1.0
Dimensional Category	DW1	Durability Class	Exposure Grade
Average Weight / Unit (kg)	2.5	Liability to Efflorescence	Slight
Core Volume (%)	Solid	Lime Pitting Liability	Slight
Units per Square Metre	69.5	Solar Absorption	0.73
Pack Size	700	LRV	11.1
Characteristic Unconfined Compressive Strength (f 'uc) MPa	>8	Solar Absorption	0.73

A BRAND OF

BRICKWORKS