























Bowral 76 Range Technical Data Sheet

BRICKWORKS

Product Range	Product Name	Dimension Illustration	Swatch	State	Length (mm)	Width (mm)	Height (mm)	Dimensional Category	Units per Square Metre	Pack Size	Characteristic Unconfined Compressive Strength (f _{uc}) MPa	Maximum Cold Water Absorption (%)	Initial Rate of Absorption (IRA) (kg/m ² min)	Coefficient of Expansion Factor (mm/m)	Durability Class	Liability to Efflorescence	Lime Pitting Liability	LRV
Bowral 76	Bowral Blue			SQLD	230	110	76	DW1	48.5	384	>12	15	1.0-8.0	1.2	Exposure Grade	Nil to slight	Nil to slight	8.3
Bowral 76	Bowral Brown			SQLD	230	110	76	DW1	48.5	384	>12	15	1.0-8.0	1.2	Exposure Grade	Nil to slight	Nil to slight	14.7
Bowral 76	Brahman Granite			SQLD	230	110	76	DW1	48.5	384	>12	15	1.0-8.0	1.2	Exposure Grade	Nil to slight	Nil to slight	11.6
Bowral 76	Capitol Red			SQLD	230	110	76	DW1	48.5	384	>12	15	1.0-8.0	1.2	Exposure Grade	Nil to slight	Nil to slight	14.9
Bowral 76	Chillingham White			SQLD	230	110	76	DW1	48.5	384	>8	15	1.0-8.0	1.2	Exposure Grade	Nil to slight	Nil to slight	56.1
Bowral 76	Embassy Red			SQLD	230	110	76	DW1	48.5	384	>12	15	1.0-8.0	1.2	Exposure Grade	Nil to slight	Nil to slight	11.1
Bowral 76	Gertrudis Brown			SQLD	230	110	76	DW1	48.5	384	>12	15	1.0-8.0	1.2	Exposure Grade	Nil to slight	Nil to slight	11.9
Bowral 76	Hereford Bronze			SQLD	230	110	76	DW1	48.5	384	>8	15	1.0-8.0	1.2	Exposure Grade	Nil to slight	Nil to slight	17.3
Bowral 76	Murray Grey			SQLD	230	110	76	DW1	48.5	384	>12	15	1.0-8.0	1.2	Exposure Grade	Nil to slight	Nil to slight	17.3
Bowral 76	Renovation Gertrudis Brown			SQLD	230	110	76	DW1	48.5	500	>8	15	1.0-8.0	1.2	Exposure Grade	Nil to slight	Nil to slight	12.9
Bowral 76	Simmental Silver			SQLD	230	110	76	DW1	48.5	384	>12	15	1.0-8.0	1.2	Exposure Grade	Nil to slight	Nil to slight	28.5

This Data represents average results from commercial production lots.

If specific test results are required, sample should be taken from current production lots.

AUSTRALIAN STANDARD TEST METHODS AS/NSZ 4456 ARE USED AS APPLICABLE.

BOWRAL BRICKS