



Bowral Gable Range Technical Data Sheet



| Product Range | Product Name | Swatch | State | Length (mm) | Width (mm) | Height (mm) | Dimensional Category | Average Weight / Unit (kg) | Units per Square Metre | Characteristic Unconfined Compressive Strength (f'uc) MPa | Maximum Cold Water Absorption (%) | Initial Rate of Absorption (IRA) (kg/m2 min) | Coefficient of Expansion e Factor (mm/m) | Durability Class | Liability to Efflorescence | Lime Pitting Liability |
|---------------|----------------|---|-------|-------------|------------|-------------|----------------------|----------------------------|------------------------|---|-----------------------------------|--|--|------------------|----------------------------|------------------------|
| Bowral Gable | Stack Bond |  | SQLD | 230 | 125 | 76 | DW1 | 4 | 48.5 | >8 | 15 | 4.0-6.0 | 1.0 | Exposure Grade | Slight | Slight |
| Bowral Gable | Stretcher Bond |  | SQLD | 230 | 125 | 76 | DW1 | 4 | 48.5 | >8 | 15 | 4.0-6.0 | 1.0 | Exposure Grade | Slight | Slight |

This Data represents average results from commercial production lots.
If specific test results are required, sample should be taken from current production lots.
AUSTRALIAN STANDARD TEST METHODS AS/NSZ 4456 ARE USED AS APPLICABLE.