

Bowral Highlands Range Technical Data Sheet

BRICKWORKS

Product Range	Product Name	Dimension Illustration	Swatch	State	Length (mm)	Width (mm)	Height (mm)	Dimensional Category	Units per Square Metre	Pack Size	Characteristic Unconfined Compressive Strength (f _{uc}) MPa	Maximum Cold Water Absorption (%)	Initial Rate of Absorption (IRA) (kg/m ² min)	Coefficient of Expansion Factor (mm/m)	Durability Class	Liability to Efflorescence	Lime Pitting Liability	LRV
Bowral Highlands	Meryla			SQLD	230	110	76	DW1	48.5	384	>8	15	1 to 8	1.2	Exposure Grade	Slight	Slight	27.8
Bowral Highlands	Penrose			SQLD	230	110	76	DW1	48.5	384	>8	15	1 to 8	1.2	Exposure Grade	Slight	Slight	
Bowral Highlands	Bangadilly			SQLD	230	110	76	DW1	48.5	384	>8	15	1 to 8	1.2	Exposure Grade	Slight	Slight	11.9
Bowral Highlands	Wingello			SQLD	230	110	76	DW1	48.5	384	>8	15	1 to 8	1.2	Exposure Grade	Slight	Slight	28.33
Bowral Highlands	Burrawang			SQLD	230	110	76	DW1	48.5	384	>8	15	1 to 8	1.2	Exposure Grade	Slight	Slight	
Bowral Highlands	Welby			SQLD	230	110	76	DW1	48.5	384	>8	15	1 to 8	1.2	Exposure Grade	Slight	Slight	

This Data represents average results from commercial production lots.
 If specific test results are required, sample should be taken from current production lots.
 AUSTRALIAN STANDARD TEST METHODS AS/NSZ 4456 ARE USED AS APPLICABLE.

BOWRAL BRICKS