

Range: Bowral Blends

Colour: Kangaloon

SKU: bowral_blends_kangaloon

Technical Data

Length (mm)	230	Maximum Cold Water Absorption (%)	<15
Width (mm)	110	Initial Rate of Absorption (IRA) (kg/m ² min)	3.0-8.0
Height (mm)	76	Coefficient of Expansion e'Factor (mm/m)	<1.0
Dimensional Category	DW1	Durability Class	Exposure Grade
Average Weight / Unit (kg)	3.8	Liability to Efflorescence	Slight
Core Volume (%)	Solid	Lime Pitting Liability	Slight
Units per Square Metre	48.5	Solar Absorption	0.83
Pack Size	400	LRV	11.9
Characteristic Unconfined Compressive Strength (f 'uc) MPa	>12	Solar Absorption	0.83

A BRAND OF

BRICKWORKS