Bowral Gable Range Technical Data Sheet

BRICKWORKS

Product Range	Product Name	Swatch	State	Length (mm)	Width (mm)	Height (mm)	Dimensional Category	Average Weight / Unit (kg)	Units per Square Metre	Characteristic Unconfined Compressive Strength (f 'uc) MPa	Maximum Cold Water Absorption (%)	Initial Rate of Absorption (IRA) (kg/m2 min)	Coefficient of Expansion e'Factor (mm/m)	Durability Class	Liability to Efflorescence	Lime Pitting Liability
Bowral Gable	Stack Bond		TAS	230	125	76	DW1	4	48.5	>8	15	4.0-6.0	1.0	Exposure Grade	Slight	Slight
Bowral Gable	Stretcher Bond		TAS	230	125	76	DW1	4	48.5	>8	15	4.0-6.0	1.0	Exposure Grade	Slight	Slight

This Data represents average results from commercial production lots.

If specific test results are required, sample should be taken from current production lots. AUSTRALIAN STANDARD TEST METHODS AS/NSZ 4456 ARE USED AS APPLICABLE.