





Bowral 76 Range Technical Data Sheet

BRICKWORKS

| Product Range | Product Name               | Dimension Illustration                                                            | Swatch                                                                            | State | Length (mm) | Width (mm) | Height (mm) | Dimensional Category | Units per Square Metre | Pack Size | Characteristic Unconfined Compressive Strength (f'uc) MPa | Maximum Cold Water Absorption (%) | Initial Rate of Absorption (IRA) (kg/m2 min) | Coefficient of Expansion e Factor (mm/m) | Durability Class | Liability to Efflorescence | Lime Pitting Liability | LRV   |
|---------------|----------------------------|-----------------------------------------------------------------------------------|-----------------------------------------------------------------------------------|-------|-------------|------------|-------------|----------------------|------------------------|-----------|-----------------------------------------------------------|-----------------------------------|----------------------------------------------|------------------------------------------|------------------|----------------------------|------------------------|-------|
| Bowral 76     | Bowral Blue                |  |  | VIC   | 230         | 110        | 76          | DW1                  | 48.5                   | 384       | >12                                                       | 10                                | 1 to 8                                       | 1.2                                      | Exposure Grade   | Nil to slight              | Nil to slight          | 7.78  |
| Bowral 76     | Bowral Brown               |  |  | VIC   | 230         | 110        | 76          | DW1                  | 48.5                   | 384       | >12                                                       | 10                                | 1 to 8                                       | 1.2                                      | Exposure Grade   | Nil to slight              | Nil to slight          | 14.11 |
| Bowral 76     | Brahman Granite            |  |  | VIC   | 230         | 110        | 76          | DW1                  | 48.5                   | 384       | >12                                                       | 10                                | 1 to 8                                       | 1.2                                      | Exposure Grade   | Nil to slight              | Nil to slight          | 10    |
| Bowral 76     | Capitol Red                |  |  | VIC   | 230         | 110        | 76          | DW1                  | 48.5                   | 384       | >12                                                       | 10                                | 1 to 8                                       | 1.2                                      | Exposure Grade   | Nil to slight              | Nil to slight          | 16.78 |
| Bowral 76     | Chillingham White          |  |  | VIC   | 230         | 110        | 76          | DW1                  | 48.5                   | 384       | >8                                                        | 15                                | 1 to 8                                       | 1.2                                      | Exposure Grade   | Nil to slight              | Nil to slight          | 66.44 |
| Bowral 76     | Embassy Red                |  |  | VIC   | 230         | 110        | 76          | DW1                  | 48.5                   | 384       | >8                                                        | 15                                | 1 to 8                                       | 1.2                                      | Exposure Grade   | Nil to slight              | Nil to slight          | 11.1  |
| Bowral 76     | Gertrudis Brown            |  |  | VIC   | 230         | 110        | 76          | DW1                  | 48.5                   | 384       | >12                                                       | 10                                | 1 to 8                                       | 1.2                                      | Exposure Grade   | Nil to slight              | Nil to slight          | 11.44 |
| Bowral 76     | Hereford Bronze            |  |  | VIC   | 230         | 110        | 76          | DW1                  | 48.5                   | 384       | >12                                                       | 10                                | 1 to 8                                       | 1.2                                      | Exposure Grade   | Nil to slight              | Nil to slight          | 17.33 |
| Bowral 76     | Murray Grey                |  |  | VIC   | 230         | 110        | 76          | DW1                  | 48.5                   | 384       | >12                                                       | 10                                | 1 to 8                                       | 1.2                                      | Exposure Grade   | Nil to slight              | Nil to slight          | 18    |
| Bowral 76     | Renovation Gertrudis Brown |  |  | VIC   | 230         | 110        | 76          | DW1                  | 48.5                   | 500       | >12                                                       | 10                                | 1 to 8                                       | 1.2                                      | Exposure Grade   | Nil to slight              | Nil to slight          |       |
| Bowral 76     | Simmental Silver           |  |  | VIC   | 230         | 110        | 76          | DW1                  | 48.5                   | 384       | >8                                                        | 15                                | 1 to 8                                       | 1.2                                      | Exposure Grade   | Nil to slight              | Nil to slight          | 33.33 |

This Data represents average results from commercial production lots.  
If specific test results are required, sample should be taken from current production lots.  
AUSTRALIAN STANDARD TEST METHODS AS/NSZ 4456 ARE USED AS APPLICABLE.